

UPM Raflatac Technical Information

23-04-2023 EN SI

Product	THERMAL ECO BPA FREE-FSC / RP51 / HONEY GLASSINE 65
Sales Code	BZE/RP5X/03
EAN	6415788105894
Product use	Product designed for general purpose non topcoated direct thermal labels for retail and transport & logistics applications with good convertability, direct thermal printability and ambient temperature performance.

Typical technical values

Face	THERMAL ECO BPA FREE-FSC			
Product	A non-top coated paper with a high sensitivity thermal coating produced totally without BPA-based chemistry. This face paper is made from FSC™-certified (mix credit) pulp. Limited resistance to thermal image scratching or smudging.			
Substance	67	g/m ²	ISO 536	
Caliper	75	µm	ISO 534	
Tensile strength MD	3,4	kN/m	ISO 1924/2	min
Tensile strength CD	2,3	kN/m	ISO 1924/2	min
Brightness	92	%	ISO 2470/3	norm
Roughness	1,9	µm	ISO 8791	PPS 10
Imaging colour	Black			
Scanning	Visible red light (wavelength up to 650 nm).			
DT printing speed	Direct thermal printing speed up to 300 mm/s.			
Optical density	Direct thermal print 1.27 (min)			
Printability	Suitable for direct thermal and water based flexography.			
Sustainability	The product is sold as FSC Mix Credit under UPM Raflatac's FSC™ certificate SGSCH-COC-004879.			
Regulatory info	Face material contains the substance 4,4'-sulphonyldiphenol (Bisphenol S) CAS no: 80-09-1 which is included on the candidate list of Substances of Very High Concern (SVHC) for authorization, according to article 59 (1, 10) of the REACH registration regulation (EC) No 1907/2006 in a concentration above 0.1% (w/w).			

Adhesive	RP51		
Type	General purpose permanent adhesive.		
Composition	Acrylic, water borne.		
Tack	18	N/25mm	FTM 9

Backing	HONEY GLASSINE 65			
Product	Yellow transparent glassine backing paper.			
Substance	55	g/m ²	ISO 536	
Caliper	49	µm	ISO 534	
Tensile strength MD	6	kN/m	ISO 1924	



Tensile strength CD	2,3	kN/m	ISO 1924
Transparency	49	%	DIN 53147

Performance

Total caliper	143
Minimum labelling temperature	0 °C
Service temperature	-20 °C to 80 °C
Shelf life	From date of manufacture: 24 months, under FINAT defined storage conditions (+20-25°C and RH 40-50%). Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life.

Information

Product Information	General purpose product for retail and transport & logistics applications. Good adhesion to all normal substrates, including non-polar surfaces, films and corrugated boards. Good low temperature performance. Not suitable for labelling plasticized PVC and the product has limited resistance in wet conditions. Not recommended for labelling highly curved surfaces.
---------------------	--

Approvals

Approvals	For further compliance information related to food labeling applications, please contact your local sales representative for a Declaration of Conformance (DoC) document.
-----------	---

Disclaimer	The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.
------------	---

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.

